



ACERINOX EUROPA FABRICA DEL CAMPO DE GIBRALTAR PALMONES (LOS BARRIOS) TFNO. (34) - 956 62 93 00 FAX (34) - 956 62 93 11 P.O. BOX 93 11370 LOS BARRIOS (CADIZ) ESPAÑA	 by Accredited Body	INSPECTION CERTIFICATE CERTIFICADO DE INSPECCION		3.1 CERTIFICATE N° F0 2020 34025 30002 * CERTIFICADO N°																		
CUSTOMER CLIENTE OIKI ACCIAI INOSSIDABILI SPA VIA PARADIGNA, 95/A 43100 PARMA ITALIA		OUR ORDER N° N° PEDIDO SO 96495	YOUR ORDER N° S° PEDIDO BO-276-ORD. 254+255+186																			
REQUIREMENTS NORMAS APLICABLES EN 10028-7/TRD 100/AD-2000-MERKBLATT W0/W2/W10 PED2014/68/EU EN 10088-2:2014 ASTM A240Ed19/A480Ed19-ASME SecIIA SA240/SA480Ed19 EN 10088-2:2014 ASTM A240Ed20/A480Ed20-ASME SecIIA SA240/SA480Ed19		INTERGRANULAR CORROSION GRADE CORROSION INTERGRANULAR EN ISO 3651-2 EN ISO 3651-2 ASTM-A-262 PRACTICA E EN ISO 3651-2 ASTM-A-262 PRACTICA E	STEELMAKING PROCESS PROCESO DE ACERIA 4511 A.O.D.																			
COIL / BOX BOBINA / CAJA 010BZR D 020BZR A 020BZR B	CONTENT CONTENIDO 010BZR D 020BZR A 020BZR B	DIMENSIONS (mm) DIMENSIONES <table border="1" style="width:100%; border-collapse: collapse;"> <thead> <tr> <th>THICKNESS</th> <th>WIDTH</th> <th>LENGTH</th> </tr> <tr> <th>ESPESOR</th> <th>ANCHO</th> <th>LARGO</th> </tr> </thead> <tbody> <tr> <td>4,000</td> <td>1500,00</td> <td></td> </tr> <tr> <td>4,000</td> <td>1500,00</td> <td></td> </tr> <tr> <td>4,000</td> <td>1500,00</td> <td></td> </tr> </tbody> </table>		THICKNESS	WIDTH	LENGTH	ESPESOR	ANCHO	LARGO	4,000	1500,00		4,000	1500,00		4,000	1500,00		MARKS MARCA 4 2 3	QUANTITY CANTIDAD 1 1 1	TEST N° PROBETA 010BZR 020BZR 020BZR	FINISH ACABADO 2B 2B 2B 2B 2B
THICKNESS	WIDTH	LENGTH																				
ESPESOR	ANCHO	LARGO																				
4,000	1500,00																					
4,000	1500,00																					
4,000	1500,00																					
CHEMICAL ANALYSIS / COMPOSICIÓN QUÍMICA (%)																						
HEAT N° COLADA 0BZR	C	CR	MN	MO	N	NI	P	S	SI	CO	CU											
	0,014	16,715	1,405	2,058	0,044	10,155	0,030	0,001	0,348	0,337	0,479											
MECHANICAL PROPERTIES / CARACTERÍSTICAS MECÁNICAS																						
TEST N° PROBETA 010BZR 010BZR 020BZR 020BZR	PROBE ST. TYPE C.T. F.T. C.T. F.T.	Rm N/mm2 609,73 596,20	Rp 0.2 N/mm2 321,90 308,63	Rp 1.0 N/mm2 352,67 339,18	A50 % 52,96 53,78	A5 % 54,96 55,78	HRB 81,00 82,00 80,00 79,00															
REMARKS / OBSERVACIONES Spectrochemical identity test O.K. Heat treatment: 1050-1100°C. Cooling with air. Issued in agreement with TÜV SÜD Industrie Service GmbH (02/1983). The delivery is in accordance with the order Temperatura de hipertemple entre 1050 y 1100 ° C. NACE-MR0175/ISO 15156-3:2015;NACE MR0103:2012/ISO 17945:2015 (Chem & Mech only). MATERIAL FREE OF RADIOACTIVITY										SURFACE AND DIMENSIONAL CONTROL INSPECCIÓN SUPERFICIAL Y DIMENSIONAL SATISFACTORY SATISFACTORIA												
WORK INSPECTOR INSPECTOR  A. Heredia										Palmones, 26 Noviembre 2020												

ACERINOX EUROPA FABRICA DEL CAMPO DE GIBRALTAR PALMONES (LOS BARRIOS) TFNO. (34) - 956 62 93 00 FAX (34) - 956 62 93 11 P.O. BOX 83 11370 LOS BARRIOS (CADIZ) ESPAÑA	 by Accredited Body	 0769-CPR-VAS-00530 DoP no. 1/2015	INSPECTION CERTIFICATE CERTIFICADO DE INSPECCION 3.1														
CUSTOMER CLIENTE OIKI ACCIAI INOSSIDABILI SPA VIA PARADIGNA, 95/A 43100 PARMA ITALIA			OUR ORDER N° N° PEDIDO SO 96495		YOUR ORDER N° S/ PEDIDO BO-276-ORD. 254+255+186												
TRADE MARK SELLO DEL FABRICANTE 			INSPECTOR'S STAMP SELLO DEL INSPECTOR		STEELMAKING PROCESS PROCESO DE ACERÍA A.O.D.												
REQUIREMENTS NORMAS APLICABLES EN 10088-4:2009			INTERGRANULAR CORROSION GRADE CORROSIÓN INTERGRANULAR		MATERIAL Acx 240 1.4404		FINISH ACABADO 2B										
COIL / BOX BOBINA / CAJA 010BZR D 020BZR A 020BZR B	CONTENT CONTENIDO 010BZR D 020BZR A 020BZR B	DIMENSIONS (mm) DIMENSIONES			MARKS MARCA 4 2 3	QUANTITY CANTIDAD 1 1 1	TEST N° PROBETA 010BZR 020BZR 020BZR	C C C									
CHEMICAL ANALYSIS / COMPOSICIÓN QUÍMICA (%)																	
HEAT N° COLADA	C	CR	MN	MO	N	NI	P	S	SI	CO	CU						
REQUIREMENTS REQUISITOS	0,030	16,500 18,500	2,000	2,000 2,500	0,100	10,000 13,000	0,045	0,015	1,000								
0BZR	0,014	16,715	1,405	2,058	0,044	10,155	0,030	0,001	0,348	0,337	0,479						
MECHANICAL PROPERTIES / CARACTERÍSTICAS MECÁNICAS																	
TEST N° PROBETA	SIT SIT	Rm N/mm2	Rp 0.2 N/mm2	Rp 1.0 N/mm2	A5 %	HRB											
REQUIREMENTS REQUISITOS		530,00 680,00	240,00	270,00	40,00												
010BZR	C T	609,73	321,90	352,67	54,96	81,00											
020BZR	C T	596,20	308,63	339,18	55,78	80,00											
REMARKS / OBSERVACIONES The delivery is in accordance with the order MATERIAL FREE OF RADIOACTIVITY									SURFACE AND DIMENSIONAL CONTROL INSPECCIÓN SUPERFICIAL Y DIMENSIONAL Satisfactory SATISFACTORIA								
									WORK INSPECTOR INSPECTOR  A. Heredia								
									Palmones, 26 Noviembre 2020								